

# ABSTRACT

A monoazo lake pigment composition containing a monoazolakepigment obtained from a laked pigment aqueous slurry  
5 prepared by conducting coupling of a diazo component obtained by diazotizing an aromatic amine having a soluble group and a coupler component and conducting laking after or simultaneously with the coupling, wherein the laking is carried out in the presence of a water-soluble acrylic polymer in an  
10 amount of 0.1 to 40 parts by weight per 100 parts of the above coupler component, and a gravure ink containing the above pigment composition and a gravure ink vehicle.